

### OPERE DI LATTONERIA IN RAME

SVILUPPO IN CM	SPESSORE IN MM		
	PESO PER 1 M (IN KG)		
	10/10	8/10	6/10
20	1,778	1,422	1,067
25	2,222	1,778	1,334
30	2,667	2,134	1,600
33	2,934	2,347	1,760
35	3,111	2,489	1,867
40	3,556	2,845	2,134
50	4,445	3,556	2,667
60	5,334	4,267	3,201
67	5,956	4,765	3,574
70	6,223	4,978	3,734
75	6,667	5,334	4,000
80	7,112	5,690	4,268
100	8,890	7,112	5,334