

### OPERE DI LATTONERIA IN ZINCATO - PVF

SVILUPPO IN CM	SPESSORE IN MM		
	PESO PER 1 M (IN KG)		
	10/10	8/10	6/10
20	1,570	1,250	0,940
25	1,960	1,560	1,175
30	2,355	1,875	1,410
33	2,590	2,060	1,550
35	2,756	2,190	1,645
40	3,140	2,500	1,880
50	3,925	3,125	2,350
60	4,710	3,750	2,820
67	5,260	4,190	3,150
70	5,495	4,375	3,290
75	5,890	4,690	3,525
80	6,280	5,000	3,760
100	7,850	6,250	4,700
120	9,420	7,550	5,640